

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L2	5687	(imad adj3 qashou) or (joesph adj3 merker) or (polymer group)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:41
L3	406515	((("442") or ("428") or ("51") or ("15"))).CLAS.	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	OR	OFF	2005/11/13 12:41
L4	9	(abrasive same nonwoven same meltblown same filaments)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:43
L5	230	absorbent same nonwoven same staple same polypropylene same card\$3	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:43
L6	1	I4 and I5	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:42
L7	1319	abrasive and nonwoven and (meltblown same fiber or filament)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:43
L8	739	absorbent and nonwoven and (staple same polypropylene same card\$3)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:43
L9	35	I7 and I8	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:43
L10	24	I9 and ((bond\$3 same unbond\$3) or (bond\$3 same pattern))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:48
L11	14	I10 and (crenulation or bunching or wave pattern or pillow\$3 or slip\$5)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 13:14

L12	0	I10 and (coefficient of friction)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:49
L13	0	I10 and (coefficient of friction)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:50
L14	3	I10 and (friction)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 12:50
L15	101	I3 and ((abrasive same nonwoven) and (absorbent same nonwoven))	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 13:13
L16	10	I2 and I15	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 13:13
L17	17	I15 and (crenulation or bunching or wave pattern or pillow\$3 or slip\$5)	US-PGPUB; USPAT; USOCR; EPO; JPO; DERWENT	ADJ	ON	2005/11/13 13:14